

SPECIFICATION

| | |
|--|---|
| FABRIC: | Style 315 Proban® / FR-7A® 100% Cotton U.S.S. Whipcord |
| WIDTH – (Inches, Minimum, Selvedge included): ASTM D3774 | 59 |
| YARNS PER INCH – (Minimum, Warp and Fill): ASTM D3775 | 64 x 36 |
| WEIGHT – (Oz/sq yd, Minimum): ASTM D3776 | 12.0 |
| BREAKING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D5034 | 130 x 90 |
| TEARING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D1424 | 5.0 x 5.0 |
| SHRINKAGE – (% , Maximum): Federal Test Method Standard 191A Method 5550 Warp and Fill | 3.0 |
| FLAMMABILITY: ASTM D 6413 | |
| After Flame, Seconds (Maximum) | 2.0 |
| Char Length, Inches (Maximum) | 5.0 |

FR-7A® is a trademark of Westex Inc.
PROBAN® is a trademark of Rhodia